

# K888 POWER

www.hipac.it

LLDPE stretch film for use on automatic machines equipped with pre-stretch group; suitable for general application

Characteristics	Method	Measurement Unit	Values
Thickness	-	Micron	23
Density	ASTM D-1505	gr/cc	0,916-0,920
Impact resistance (Dart test)	ASTM D-1709	gr.	190
Tensile strength at Yield	ASTM D-882 B	N/mm2	10
MD ↓			
	ASTM D-882 B	N/mm2	9
TD →			
Tensile strength at break	ASTM D-882 B	M Pa	36
MD ↓			
	ASTM D-882 B	M Pa	24
TD →			
Elongation at break	ASTM D-882 B	%	502
MD ↓			
	ASTM D-882 B	%	646
TD →			
Tear resistance (Elmendorf)	ASTM D-1922	mN	3274
MD ↓			
	ASTM D-1922	mN	4680
TD →			
Guaranteed pre-stretch	Hipac Method	%	240
Max pre-stretch	Hipac Method	%	250
Cling	Hipac Method	g	130

Rel. 2008

Hipac Laboratory

In case of coloured stretch film these values can vary depending on the percentage of masterbatch used.

The above values are the result of standard tests made in our laboratory. They are to be considered as indicative in order to facilitate the choice and the utilisation for each sector, but are not given for guaranty purposes. Hipac reserves the right to modify them, if necessary, without notice.



NETROLL OXOLL Are trade marks

STRETCH FILM FOR INDUSTRIAL AND FOOD PACKAGING