

308 A/J STANDARD

LLDPE cast stretch film, suitable for wrapping machines without prestretch group.

| Characteristic | Method | Unit | Direction | 12 µm | 15 µm | 17 µm | 20 µm | 23 µm | 30 µm | 35 µm | 50 µm | Tolerances |
|---------------------------|--------------|------|-----------------------|-------|-------|-------|-------|-------|-------|-------|-------|------------|
| Impact resistance | ASTM D1709 A | g | - | 40 | 50 | 70 | 75 | 85 | 100 | 125 | 147 | 10% |
| Tensile strength at break | ASTM D882 B | MPa | Machine Direction | 22 | 27 | 30 | 32 | 32 | 33 | 35 | 42 | 10% |
| | | | Transversal Direction | 17 | 17 | 18 | 18 | 20 | 22 | 22 | 29 | 10% |
| Tensile strength at yield | ASTM D882 B | MPa | Machine Direction | 6 | 6,5 | 6,5 | 6,5 | 6,5 | 7 | 7 | 8 | 10% |
| | | | Transversal Direction | 4,5 | 5 | 5 | 5 | 5,5 | 6 | 6,5 | 7,5 | 10% |
| Elongation at break | ASTM D882 B | % | Machine Direction | 400 | 420 | 430 | 460 | 480 | 550 | 600 | 730 | 10% |
| | | | Transversal Direction | 500 | 550 | 570 | 600 | 650 | 670 | 680 | 780 | 10% |
| Tear Resistance | ASTM D1922 | mN | Machine Direction | 1600 | 1700 | 2100 | 2200 | 2500 | 2700 | 3000 | 4100 | 10% |
| | | | Transversal Direction | 2300 | 2350 | 2712 | 3200 | 3220 | 3300 | 3300 | 4650 | 10% |
| Stretch | Hipac | % | - | 60 | 70 | 90 | 110 | 145 | 170 | 180 | 220 | 5% |
| Cling | Hipac | g | - | 135 | 135 | 135 | 130 | 130 | 125 | 120 | 115 | 10% |

In case of coloured stretch film these values should be reduced by 10%.
 In case of additives these values should be reduced by 5%.
 In case of printed film these values should be reduced by 5%.

| Coloured | Slippery | AUV 6/12 months | Antistatic | Net Roll | Cling Out/In/Both | Printed |
|---|---|---|---|---|---|---|
|  |  |  |  |  |  |  |

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification.

HIPAC SpA: Via per Rovato, 10 25046 Cazzago San Martino (Brescia) ITALY Phone: +39 030 7750610 Fax:+39 030 7750847.
IBERHIPAC SA: Crta N-V Km 189,1 10390 Saucedilla (Cáceres) - SPAIN Phone: +34 927 545188 Fax:+34 927 545187.
HIPAC ROMANIA srl: Dragomiresti Vale, Ilfov (Bucarest) – ROMANIA Phone: +40 21 3523600 Fax:+40 21 3523608.