

# 999 A/M EXTRA RIGID

LLDPE cast stretch film mechanically pre-stretched to very low thickness. Specially indicated where there are light and/or easily deformable goods. Slippery outside and cling inside. **To be used only on wrapping machines WITHOUT prestretch group or for manual use.**

Characteristic	Method	Unit	Direction	5 µm	6 µm	7 µm	8 µm	9 µm	10 µm	Tolerances
Impact resistance	ASTM D1709 A	g	-	33	35	39	41	44	47	10%
Tensile strength at break	ASTM D882 B	MPa	Machine Direction	73	74	75	76	76	77	10%
			Transversal Direction	19	19	20	20	21	21	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine Direction	37	38	38	38	39	40	10%
			Transversal Direction	5	5	5	5	5,5	5,5	10%
Elongation at break	ASTM D882 B	%	Machine Direction	122	120	130	135	140	145	10%
			Transversal Direction	710	735	750	800	825	850	10%
Tear Resistance	ASTM D1922	mN	Machine Direction	965	980	1010	1030	1045	1060	10%
			Transversal Direction	2410	2400	2410	2450	2480	2550	10%
Stretch	Hipac	%	-	10	10	10	15	20	25	5%
Cling	Hipac	g	-	125	125	125	125	125	125	10%

Coloured	AUV 6/12 months	Antistatic	NetRoll	Cling Out/In/Both	Printed
✘	✘	✘	✔	✘	✘

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification.

**HIPAC SpA:** Via per Rovato, 10 25046 Cazzago San Martino (Brescia) **ITALY** Phone: +39 030 7750610 Fax:+39 030 7750847.

**IBERHIPAC SA:** Crta N-V Km 189,1 10390 Saucedilla (Cáceres) - **SPAIN** Phone: +34 927 545188 Fax:+34 927 545187.

**HIPAC ROMANIA srl:** Dragomiresti Vale, Ilfov (Bucarest) – **ROMANIA** Phone: +40 21 3523600 Fax:+40 21 3523608.