

Description:

Hipac stretch film is an oriented linear-low-density polyethylene film obtained by cast-extrusion technology through flat-die.

Characteristics:

This kind of technology allows obtaining a product with a low crystalline content and consequently the highest transparency and elasticity. The properties of the different films are reported in our technical data-sheets. The tolerances of our finished products are described in our Technical specification sheet.

Application:

Hipac stretch film is suitable for manual or automatic application on all pallet wrapping machines available on the market.

Storage:

Although Hipac stretch film is made of very stable polymers with high molecular weight, it is highly recommended to take the necessary precautionary measures as follows:

- Do not store under direct sun light, at a temperature lower than 0°C or higher than 40°C.
- Just to avoid coil damages, the film must be kept in a dry area.
- Clean and hygienic storage and packaging conditions are suggested.
- Since all the technical characteristics of the film (such as Tensile Strength, Elongation, Tear Resistance and Dart Drop) change in the long run, the storage-time should not exceed 3 months from the delivery date.

Usage:

The range of temperature where the stretch film maintains its mechanical properties goes from 0°C to 40°C. Below or above those values, the film mechanical properties can vary. If you need to use the film below 0°C or above 40°C do not hesitate to contact HIPAC in order to get the best solution.

HIPAC Group

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice.

HIPAC SpA: Via per Rovato, 10 25046 Cazzago S. Martino (Brescia) **ITALY** Phone: +39 030 7750610 Fax:+39 030 7750847.
IBERHIPAC SA: Crta N-V Km 189,1 10390 Saucedilla (Cáceres) - **SPAIN** Phone: +34 927 545188 Fax:+34 927 545187.
HIPAC ROMANIA srl: Dragomiresti Vale, Ilfov (Bucharest) – **ROMANIA** Phone: +40 21 3523600 Fax:+40 21 3523608.